

DATA SHEET

TX24/14/8.9

Powder material toroids

New data

2007 Jan 01



FERROXCUBE
A YAGEO COMPANY

RING CORES (TOROIDS)

Effective core parameters


SYMBOL	PARAMETER	VALUE	UNIT	
$\Sigma(l/A)$	core factor (C1)	1.52	mm ⁻¹	
V_e	effective volume	2280	mm ³	
l_e	effective length	58.8	mm	
A_e	effective area	38.8	mm ²	
m	mass of core (for μ_i 125)	MPP	19.9	g
		Sendust	14.0	g
		High-Flux	18.8	g

Coating

The cores are coated with epoxy. The colour is cream (Sendust), grey (MPP) or khaki (High-Flux). Maximum operating temperature is 200 °C.

Isolation voltage

AC isolation voltage : 1000 V.
Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A_L (nH)	μ_i	TYPE NUMBER
MPP	12 ± 8 %	14	TX24/8.9-M2-A12
	22 ± 8 %	26	TX24/8.9-M2-A22
	51 ± 8 %	60	TX24/8.9-M2-A51
	105 ± 8 %	125	TX24/8.9-M2-A105
	124 ± 8 %	147	TX24/8.9-M2-A124
	135 ± 8 %	160	TX24/8.9-M2-A135
	146 ± 8 %	173	TX24/8.9-M2-A146
	169 ± 8 %	200	TX24/8.9-M2-A169
Sendust	253 ± 8 %	300	TX24/8.9-M2-A253
	22 ± 8 %	26	TX24/8.9-S7-A22
	51 ± 8 %	60	TX24/8.9-S7-A51
	105 ± 8 %	125	TX24/8.9-S7-A105

Powder material toroids

TX24/14/8.9

GRADE	A_L (nH)	μ_i	TYPE NUMBER
High-Flux	$12 \pm 8 \%$	14	TX24/8.9-H2-A12
	$22 \pm 8 \%$	26	TX24/8.9-H2-A22
	$51 \pm 8 \%$	60	TX24/8.9-H2-A51
	$105 \pm 8 \%$	125	TX24/8.9-H2-A105
	$124 \pm 8 \%$	147	TX24/8.9-H2-A124
	$135 \pm 8 \%$	160	TX24/8.9-H2-A135

Properties of cores under power conditions

GRADE	μ_i	B (mT) at	CORE LOSS (W) at
		H = 100 kA/m; f = 10 kHz; T = 25 °C	f = 100 kHz; $\hat{B} = 100$ mT; T = 25 °C
MPP	14	≥ 640	3.42
	26	≥ 700	2.74
	60	≥ 760	1.71
	125	≥ 800	1.71
	147	≥ 800	1.82
	160	≥ 800	1.82
	173	≥ 800	1.82
	200	≥ 800	3.42
	300	≥ 800	3.42
Sendust	26	≥ 1000	3.65
	60	≥ 1030	1.95
	125	≥ 1060	1.95
High-Flux	14	≥ 890	5.70
	26	≥ 980	4.56
	60	≥ 1280	4.10
	125	≥ 1370	4.56
	147	≥ 1385	5.02
	160	≥ 1400	7.98

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.